



ZETTEX

STICK WITH US

TECHNICAL DATA SHEET

Underbody Coating

Zettex Europe B.V.
Plaza 20, 4782 SK Moerdijk
The Netherlands
+31 (0)888-93 88 39
info@zettex.com
www.zettex.com

Product description

Zettex Underbody Coating spray is a black, bitumen rich, water-resistant, anti-corrosion coating for surfaces on the underside of cars. Protects against physical damage, rubble and repels moisture. Zettex Underbody Coating can be painted over with most painting systems.

Advantages

- Excellent anti-corrosion properties.
- Primer not required.
- Semi-flexible coating, resistant to cracks.
- Excellent resistance to water and salt.
- 360-degree usability ensures that Underbody Coating can even be applied on surfaces that are difficult to reach.
- Can be painted over

Uses

- For use on sills, wheel housings, fuel tanks, sub-frames and chassis.
- Not for use on decorative applications, rubber and plastic surfaces or pre-coated surfaces.

Application instructions

First thoroughly clean the surface. Dust, oil, grease and other residues can be removed with Zettex Megaclean. Apply the Megaclean beforehand on the Zettex Bonte or Witte tricot cloth, allow the Megaclean to work in briefly then remove the residues. Shake the spray can for at least two minutes and repeat this when the can has not been used for a while. Apply the spray from a distance of 20-30 cm from the surface. The Zettex Underbody Coating fully dries within 24 hours, depending on the temperature and the thickness of the coating.

Available form

Spray can 500 ml

Colour

Black

Safety recommendations

This technical information does not contain an MSDS (Material Safety Data Sheet). You must first fully read the MSDS before using this product.

Properties	Specification
Appearance	Black with an aromatic odour
pH	Not applicable
Specific gravity	0.92 – 0.96
Not volatile % m/m	50 – 60
Active content % m/m, as supplied	30 – 40
Flammability, as supplied	Highly flammable, flash point below -20°C
Viscosity	2500-4000 cPs

Volatile organic constituents, as supplied	In compliance with EU directives 2004/42/CE
Application temperature	15-25 °C