



STICK WITH US

## TECHNICAL DATA SHEET

### Easy Silicone Alcoxy Sanitary



#### Zettex Europe BV

Partridgeweg 1, 4791 RV Klundert

The Netherlands

+31 (0)888-93 88 39

[info@zettex.com](mailto:info@zettex.com)

[www.zettex.com](http://www.zettex.com)

#### Product Description

Zettex Alcoxy Silicone Sanitary is a high-quality one-component sealant based on Alcoxy Crosslinking silicone (neutral system). Properties: Permanently soft, elastic. Odourless and acid-free.

Perfectly mold and bacteria resistant. High UV resistance. Suitable for food contact according to HACCP and ISEGA standards. Certified according to ISO11600- F&G 25LM. Not paintable . Durable and colorfast.

#### Material

Alcoxy silane .

#### Properties

- Insensitive to mold.
- Chemical resistant.
- Colourfast.
- Permanently elastic.
- UV resistance.
- Excellent workability.
- (sea) water resistant.

#### Applications

For sealing joints, seams and cracks in bathrooms, kitchens, toilets, showers, cars, boats and caravans.

#### Utilization

The surface must be clean, dry and free of dust and grease. Clean the surface in advance with Zettex Profi Cleaner. Any uncured sealant residue and other dirty material can be removed with Zettex Profi Cleaner . Smooth finish with Zettex Easy Finish. Always test the surface for adhesion in advance. After use, hands can be cleaned with Zettex Cleaning Wipes .

#### Packaging

- Cartridge 310 ml

#### Colour

White, black, grey, anthracite, transparent, transparent grey, ral 9001. Other colours are available on request.

#### Safety recommendations

Always read the safety information before use.

#### Shelf life

18 months in unopened packaging. Store at temperatures between 5°C and 25°C.

Properties

Specifications

Basic	Acetoxo
Hardening	2 mm per 24 hours
Processing temperature	+5°C to +40°C
UV resistance	Very good
Skin formation time	Approx. 5 minutes
Temperature resistance (cured)	-50°C to +180°C
Water resistance	excellent
Density	1.00g/ml
Elongation at break	700%
Tensile strength	1.25N/mm <sup>2</sup>
Shore A hardness	28